

H64310 | TRUST commercial Satin I90

MICROPOROUS RESIN-COATED PAPER

PRODUCT SPECIFICATION *

| | | | |
|--|------------------|------|-------|
| Weight DIN EN ISO 536 | g/m ² | 197 | ± 6 |
| Thickness DIN EN ISO 534 | µm | 203 | ± 6 |
| | mil | 8.0 | ± 0.2 |
| Gloss BYK (60°) ISO 2813 | | 19 | ± 5 |
| Colour Elrepho UVO (D65) ISO 2469 | L | 94,2 | ± 0,5 |
| | a | -0,2 | ± 0,3 |
| | b | -2,6 | ± 0,5 |
| | delta b | <0,7 | |
| il Pro2 | L*M0 | 95,3 | |
| | a*M0 | -0,3 | |
| | b*M0 | -2,7 | |
| | L*M1 | 95,3 | |
| | a*M1 | -0,3 | |
| | b*M1 | -3,0 | |
| CIE whiteness (D65/10°) min. ISO 2469 | | > 94 | |
| Opacity min. ISO 2469 | % | > 92 | |

Printability

Simplex printable

Printing Technology

💧 Inkjet water-based

Compatibility

Compatible with all commercial thermal, piezo water-based printing systems like Epson, Canon, Hewlett-Packard, Kodak, Encad etc.

Certificates



Fogra 25488-1

BENEFITS & PROPERTIES

- Reproducibility by outstanding media colour consistency
- Large colour gamut
- Pin-sharp details
- Instant dry
- Universal compatibility for printers and inks

KEY APPLICATIONS

Proof & Prepress

- Proofs for offset, gravure and screen printing
- Dot-proofs
- Contract, design and check proofs
- Mock-ups

Directions for use

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

* Modifications reserved.

Version 01/2016